

## **BITUMEN 60/70 SPECIFICATION**

| <b>Characteristic</b>               | <b>Value</b> |
|-------------------------------------|--------------|
| Specific Gravity@ 25/25 °C          | 1.01-1.06    |
| Penetration @ 25 °C                 | 60-70        |
| Softening Point °C                  | 49-56        |
| Ductility @ 25 °C                   | 100 min      |
| Loss on Heating % wt                | 0.2 max      |
| Drop in Penetration after Heating % | 20 max       |
| Flash Point °C                      | 250 min      |
| Solubility in CS <sub>2</sub> % wt  | 99.5 min     |
| Spot Test                           | Negative     |